

















Internationale Farbkennzeichnung

Kennbuchstabe	Werkstoff		DIN IEC 584	ANSI MC96.1	Temperaturbereich
	+	-			
Typ K	NiCr	- NiAl			-40 °C ... 1.000 °C
Typ J	Fe	- CuNi			-40 °C ... 750 °C
Typ N	NiCrSi	- NiSi			-40 °C ... 1.000 °C
Typ T	Cu	- CuNi			-40 °C ... 350 °C
Typ E	NiCr	- CuNi			-40 °C ... 800 °C
Typ R	Pt13%Rh	- Pt			0 °C ... 1.600 °C
Typ S	Pt10%Rh	- Pt			0 °C ... 1.600 °C
Typ B	Pt30%Rh	- Pt6%Rh			600 °C ... 1.700 °C